

# ***1125 REINFORCE KRAFT PACKAGING TAPE***

---

## **PRODUCT DESCRIPTION**

1125 Adopts Kraft – Scrim- Kraft (3 way Scrim) as backing, combined with a high performance synthetic rubber-resin adhesive, It is mainly used for carton packaging and sealing.

## **TYPICAL PHYSICAL PROPERTIES**

<b>PROPERTIES</b>	<b>METRIC</b>	<b>TEST METHOD</b>
KSK Thickness	140 Microns	PSTC-133 / ASTM D 3652
Total Thickness	170 Microns	PSTC-133 / ASTM D 3652
Adhesion to Steel	16 N/25mm	PSTC-101 / ASTM D 3330
Tensile Strength	175 N/25mm	PSTC-131 / ASTM D 3759
Elongation	5.0 %	PSTC-131 / ASTM D 3759
Service Temperature	-20 ~ +60 °C	-----
Applying Temperature	+10 ~ 40 °C	-----

## **IMPORTANT NOTE**

1. The data above are typical values only, and should not be used for specifications purpose.
2. Tolerance: Weight and Thickness:  $\pm 10\%$ ; Width:  $\pm 3\text{mm}$ ; Length: Cut Roll:  $\pm 0.3\text{m}$ , Jumbo Roll  $\pm 0.5\%$ .

**STORAGE & SHELF LIFE:** 12 months when stored at 21°C (70°F) / 50% relative humidity out of direct sunlight.

**SURFACE PREPARATION:** It is essential, as with all pressure-sensitive tapes, that the surface to which the tape is applied must be clean, dry, free of grease, oil or other contaminants.

**PRODUCT USE:** It is essential that the user evaluate the product to determine whether it is fit for a particular purpose and user's method of application. Good results will be obtained when applied to a clean, dry surface with a suitable pressure on products between +10 ~ +40°C (+50 ~ +105 °F).